


# 150.5SSC


FOR FASTENING COMPOSITE PANELS (70MM-100MM THICKNESS) TO PURLINS OF 4MM-12.5MM THICKNESS



## PROPERTIES




MATERIAL	STAINLESS STEEL A2 - 304 GRADE
COATING	500 HRS (SILVER)
HEAD TYPE	COUNTERSUNK
DRILL POINT	5 PT
EFFECTIVE THREAD LENGTH	61.00
RECOMMENDED DRILL BIT/SOCKET	BIT-T30
RECOMMENDED DRILL SPEED	1500 - 2500 RPM



## PERFORMANCE

### PULL OUT



STEEL THICKNESS (MM)	4.00	6.00	8.00	10.00	12.00
VALUE (kN)	8.90	9.50	9.50	9.50	9.50


Grade of material: S275 Steel

### PULL OVER




WASHER	16MM x 2MM		19MM x 2MM	
SHEET THICKNESS (MM)	0.50	0.70	0.50	0.70
VALUE (kN)				

### SHEAR




VALUE (kN)	8.77
------------	------

### TENSILE



VALUE (kN)	11.49
------------	-------

## DIMENSIONS



A (MM)	12.50
B (MM)	150.00
C (MM)	65.00
D (MM)	5.50
E (MM)	15.00
F (MM)	5.00
G (MM)	N/A